

Please type a plus sign (+) inside this box → ☒

PTO/SB/05 (4/98)
Approved for use through 09/30/2000. OMB 0651-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Attorney Docket No. **ACA6124PDUS**

First Inventor or Application Identifier **Larry L. Bradford**

Title **POLYURETHANE FOAM CONTAINING FLAME RETARDANT....**

Express Mail Label No. **EL246554616US**

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

1. ☒ * Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
2. ☒ Specification [Total Pages **21**]
(preferred arrangement set forth below)
 - Descriptive title of the invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the invention
 - Brief Summary of the invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☐ Drawing(s) (35 U.S.C. 113) [Total Sheets ☐
4. Oath or Declaration [Total Pages **3**]
 - a. ☒ Newly executed (original or copy)
 - b. ☐ Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 16 completed)
 - i. ☐ **DELETION OF INVENTOR(S)**
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

*** NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).**

ADDRESS TO: Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

5. ☐ Microfiche Computer Program (Appendix)
6. Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary)
 - a. ☐ Computer Readable Copy
 - b. ☐ Paper Copy (identical to computer copy)
 - c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. ☐ Assignment Papers (cover sheet & document(s))
8. ☐ 37 C.F.R. § 3.73(b) Statement ☐ Power of Attorney
(when there is an assignee)
9. ☐ English Translation Document (if applicable)
10. ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations
11. ☐ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
13. ☐ * Small Entity Statement filed in prior application, Status still proper and desired
(PTO/SB/09-12)
14. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
15. ☐ Other:

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No: _____ / _____

Prior application information: Examiner _____ Group / Art Unit: _____

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

☐ Customer Number or Bar Code Label or ☒ Correspondence address below
(Insert Customer No. or Attach bar code label here)

Name	Richard P. Fennelly				
	Akzo Nobel Inc.				
Address	Intellectual Property Department				
	7 Livingstone Avenue				
City	Dobbs Ferry	State	New York	Zip Code	10522-3408
Country	U.S.A.	Telephone	(914)674-5464	Fax	(914)693-4236

Name (Print/Type)	Richard P. Fennelly	Registration No. (Attorney/Agent)	25,677
Signature	<i>Richard P. Fennelly</i>	Date	Sept 9 1999

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

POLYURETHANE FOAM CONTAINING FLAME RETARDANT
BLEND OF NON-OLIGOMERIC AND OLIGOMERIC FLAME RETARDANTS

5 Background of the Invention

A wide variety of disclosures exists in regard to flame retardant additives for polymers, such as polyurethane foams. Two representative examples of disclosures of this type, which
10 relate to blends of two differing flame retardant additives, include the following:

U.S. Patent No. 4,273,881 to J.G. Otten describes the use of a 50:50 mixture of flame retardant A, sold under the trademark ANTIBLAZE 19, and bis-(2-chloroethyl)-2-chloroethyl-
15 phosphonate (See Col. 9, lines 61-62).

U.S. Patent No. 3,956,200 to J. Biranowski describes the use of flame retardant blends comprising a polyglycol hydrogen polyphosphonate and an additive, non-reactive flame retardant in a ratio of from about 20:1 to 1:1, preferably from about
20 5:1 to 1:1.

In addition to the foregoing patent disclosures, certain blends of monomeric and oligomeric flame retardants have also been sold to the polyurethane industry, including compositions carrying the trademarks FYROL 25 and FYROL EFF of Akzo Nobel
25 Chemicals Inc. The product sold under the former mark included an oligomer that contained a blend of both phosphate and phosphonate moieties, whereas the product sold under the latter mark contained a major amount (about 66%) of the oligomeric component and a minor (about 32.5%) of the
30 monomeric flame retardant component.

The flame retardant blends that have been previously described all contain halogen.

In addition to the foregoing, U.S. Patent No. 5,672,645 to T. Eckel et al. describes a flame retardant blend of a monophosphorus compound, which can either be halogen-
5 containing or non-halogenated, and an oligomeric phosphorus compound. This blend is only described for use in aromatic polycarbonate-containing compositions and not in polyurethane foams.

Summary of the Invention

The present invention relates to polyurethane foam compositions containing a flame retardant blend comprising:
15 (a) a non-oligomeric non-halogenated organophosphorus flame retardant that is adapted for use in a polyurethane foam formulation; and (b) an oligomeric organophosphorus flame retardant having a phosphorus content of no less than about 10%, by weight, and at least three phosphorus atom-containing
20 units therein.

Preferred blends unexpectedly pass performance tests at decreased total phosphorus level as compared to that predicted from the passing performance of the individual blend components. These blends, in some cases, are more cost
25 effective than either one of the blend components.

Description of the Preferred Embodiments

The non-oligomeric non-halogenated flame retardant that forms one essential component of the blends that are used in
30 the present invention are those flame retardants additives

that have hitherto been used in conferring flame retardancy on polyurethane foams (both flexible and non-flexible polyurethane foams).


One representative class that can be selected include the non-halogenated phosphate esters, having the formula $P(O)(OR)_3$, with R in this formula standing for an alkyl moiety containing from about one to about five carbon atoms or an aryl moiety. Representative additives which may be employed herein include: triphenyl phosphate ("TPP"); propylated or butylated TPP ("PTPP" and "BTPP", respectively); triethyl phosphate ("TEP"); tributyl phosphate ("TBP"); and the like. In addition, a non-monomeric (but non-oligomeric) phosphate containing additive (i.e., a dimer) can be selected for use herein. An example of such a dimer is: resorcinol diphosphate ("RDP").

Another type of organophosphorus additive (a) includes the non-oligomeric phosphonates species wherein one of the groups -OR in the aforementioned phosphates is replaced by the group -R. These compounds have the formula $RP(O)(OR)_2$.

The amount of such additive in the blend will range from about 25% to about 95%, by weight of the blend, more preferably from about 40% to about 70%.

The second component of the blend which is used in accordance with the present invention is an oligomeric organophosphorus flame retardant having a phosphorus content of no less than about 10%, by weight, and, in preferred embodiments when an organophosphate is desired, at least three phosphate ester units therein (i.e., at least two phosphate ester repeat units and a phosphate capping unit). The term "oligomeric" as used herein is meant to exclude either

monomeric or dimeric species. The amount of this additive in the blend will range from about 5% to about 75%, by weight of the blend, more preferably from about 30% to about 60%. A representative additive of this type is generally described in U.S. Patent No. 4,382,042 to T.A. Hardy with the non-halogenated versions being preferred (e.g., especially the ethyl group-containing composition). These preferred organophosphate oligomers can be formed by reacting phosphorus pentoxide with the selected trialkyl phosphate (e.g., triethyl phosphate) to form a polyphosphate ester containing P-O-P bonds that is then reacted with epoxide (e.g., ethylene oxide) to form the desired product. This preferred oligomeric organophosphate flame retardant is of the formula:



where n (which designates the "repeat" phosphate ester units) can range, on a number average basis, from 2 to about 20, preferably from 2 to about 10, and R is selected from the group consisting of alkyl and hydroxyalkyl and R' is alkylene. The alkyl and alkylene groups will generally contain from about two to about ten carbon atoms.

Especially preferred oligomeric phosphates for use herein will comprise ethyl and ethylene groups as the alkyl and alkylene moieties, will have a hydroxy functionality of no more than about 30 mg KOH/g, will have an acid number of no more than about 2.5 mg KOH/g, and will have a phosphorus content that ranges from about 15% to about 25%, by weight. It is referred to herein after as "PEEOP" (or "poly(ethyl ethyleneoxy)phosphate").

It is within the contemplation of the present invention to utilize oligomeric phosphonate-containing materials as component (b). Both substantially pure phosphonate and phosphonate/phosphate compositions are intended to be included. These have the same structure as depicted above for the oligomeric phosphate species with the exception that the internal (bracketed) RO- on the left side of the structure may be R- and one of the terminal -OR structures on the right side of the formula may be -R. A representative and commercially available example of an additive of this type is FYROL 51 from Akzo Nobel Chemicals Inc. which is made by a multistep process from dimethyl methylphosphonate, phosphorus pentoxide, ethylene glycol, and ethylene oxide.

The foregoing flame retardant blend is, in accordance with the present invention, added to a selected polyurethane foam formulation at from about 2 to about 35 parts by weight of the blend per 100 parts by weight of the polyol that is in the formulation. The weight percent phosphorus that is in the final polyurethane foam formulation will range from about 0.25 wt% to about 3.5 wt%. The foregoing type of flame retardant blend is especially adapted for use in flexible and rigid polyurethane foams and, in certain embodiments (e.g., at ratios of from about 1:1 to about 20:1 of the monomeric additive:oligomeric additive) in typical polyester or polyether polyurethane flexible foams, have shown unexpectedly greater efficiency of the blend as compared to the additive sums of the individual components thereof. This performance is especially attractive since the oligomeric material is typically much more expensive than the monomeric material making cost efficiency of the blend particularly beneficial.

The density of the foam is an important factor. In general, the higher the density, the less flame retardant additive required to pass the flame test. The addition of the blended product is more enhanced with this rule. For example, the primary blend of BTPP and an oligomeric phosphate ester, PEEOP, when at a 1:1 ratio will pass the TB117 test in a 1.0 pound per cubic foot (pcf) density foam at 16 parts per hundred. The same blend will meet the TB117 test in a 1.8 pcf density foam at 5 parts per hundred.

A blend of two phosphorus containing products differing in efficiency (as measured by parts required to pass a given test) can be further compared by, parts of phosphorus required to pass a given test. For blends of these two products it is expected that the phosphorus requirement to pass said test will fall between the two. If less phosphorus is required for the blend than for either individual product, it is clearly synergistic and advantageous. For example (from Data Sets 2 and 3), a monomeric flame retardant (BTPP) requires 1.36% of phosphorus to pass the TB117 test, and an oligomeric organophosphate flame retardant requires 0.95% phosphorus to meet the same test. The blend of the two products in a 1:1 ratio only requires 0.69% phosphorus in a 1.8 pcf density foam.

U.S. Patent No. 3,956,200 is incorporated herein (see, for example, Col. 6, line 25 to Col. 8, line 15) to illustrate how flexible foams, which are preferred, can be made. However, the flame retardant blend that has been previously described can be used in non-flexible polyurethane foams as well.

The foregoing invention is further illustrated by the Examples and Data Sets that follow.

EXAMPLES

The flame retardant test data that follows in the Data
5 Sets were generated using a typical polyether polyurethane
flexible foam that was tested at nominal densities of 1.0,
1.5, and 1.8 pounds per cubic foot (pcf). The formulation used
to form the foam was formed using a polyether polyol having a
hydroxyl number of 56, a water level of from 3.55% to 5.6%, an
10 amine level of about 0.25%, and an NCO index of 110.

The following standard tests were employed:

A. Cal. TB 117 A Test: This test is a small-scale
vertical test with a twelve-second-ignition time. The sample
size was 12" x 3 x 1/2". The ignition source was removed after
15 twelve seconds. A second clock is started if the sample
continues to burn. The criteria for failing included: a
sample exceeding an individual burn of eight inches or an
average burn of six inches. The time criteria required that
an individual specimen would not have an individual afterflame
20 or afterglow exceeding ten seconds or an average afterflame or
afterglow exceeding five seconds.

B. Cal. TB 117 D Test: This test is a smoldering test in
which a cigarette is used as the ignition source under a
cotton cloth cover. The foam sample was covered with a
25 standard velvet cotton cloth and was placed in a small wooden
frame to form a mock chair. The back of the sample was 8" x
7" x 2", and the seat was 8" x 4" x 2". The sample was
preweighed before testing and was again weighed after the test
was finished. If the foam lost more than 20% of its weight,
30 it was judged to be a failure.

C. MVSS 302 Test: This test is a horizontal flame test that is used as a guideline for automobile manufactures. The sample size was 14" x 4" x 1/2". There is a line 1 1/2" from the ignition point. A flame was ignited for fifteen seconds. The ignition source was then turned off and the sample was rated. A "DNI" rating indicates that the sample did not support combustion ("did not ignite"). A rating of "SE" indicates that the sample ignited but did not burn to the timing zone, which is a point starting from the 1 1/2" mark to the 3 1/2" line. A rating of "SENB" indicates that the sample burned past the 1 1/2" line but was extinguished before the 3 1/2" mark. A rating of "SE/B" indicates that a sample burned past the 3 1/2" mark but was extinguished before the endpoint. An inch per minute rate was then calculated. The burn rate indicates that a sample burned passed the 3 1/2" mark. An indication of a burn rate or an SE/B rating that was higher than 4.0 in/min indicates failure in accordance with this test. For this study a minimum performance of SENB was required.

A number of flame retardant additives were used in TB-117 and MVSS 302 tests in a variety of foams, either alone or in combination, as further described below. They were: triphenyl phosphate ("TPP"), available under the trademark PHOSFLEX TPP from Akzo Nobel Chemicals Inc.; butylated triphenyl phosphate ("BTPP"), available under the trademark PHOSFLEX 71B from Akzo Nobel Chemicals Inc.; a poly(ethyl ethyleneoxy) phosphate ("PEEOP"), of the type described in copending U.S. Serial No. 08/677,283, having a molecular weight of about 915 (number average)/1505 (weight average), a typical hydroxyl number of under about 5; and a blend of 50 wt% PHOSFLEX 71B and 50 wt%

Data Set 1

The following data illustrates that relative performance of flame retardant additives varies with foam density as well as the test method used. The described blends give unexpected synergism in some of these combinations (as density increases less flame retardant additive is usually required to meet a specific test):

Passing FR Levels* (Data Set 1)

Product	TB-117 1.0 pcf	TB-117 1.5 pcf	TB-117 1.8 pcf	MVSS 302 1.0 pcf SENBR	MVSS 302 1.5 pcf SENBR	MVSS 302 1.8 pcf SENBR
BTPP	17		16	17		14
BTPP:PEEOP 1:1	16	10	5	15	8	5
PEEOP	7	5	5	7	5	4
RDP/ PEEOP (1:1)		8	5		8	5
PHOSFLEX 4**:PEEOP (1:1)		12	7		5	5
PHOSFLEX 31 brand***/ PEEOP 1:1		9	7		7	4
TPP/PEEOP 1:1		12	7		8	4

* in parts per hundred (pph) based on 100 parts by weight of polyol used in making the foam.

** PHOSFLEX 4 flame retardant is tributyl phosphate.

*** PHOSFLEX 31 flame retardant is propylated triphenyl phosphate.

% Phosphorus Levels (Data Set 2)

Flame Retardant	%P	TB117 (phr of FR)	%P to pass in foam	MVSS 302 (phr of FR)	%P to pass in foam
--1.8 pcf Density --					
BTPP	8.5	16	1.36	14	1.19
BTPP/PEEOP	13.8	5	0.69	5	0.69
PHOSFLEX 31P/PEEOP	13.5	7	0.94	4	0.54
TPP/PEEOP	14.3	7	1.00	4	0.57
PHOSFLEX 4/PEEOP	15.4	7	1.08	5	0.77
PEEOP	19	5	0.95	4	0.76
RDP/PEEOP	15	5	0.75	5	0.75
-- 1.5 pcf Density --					
BTPP/PEEOP	13.8	10	1.38	8	1.10
PHOSFLEX 31P/PEEOP	13.5	9	1.21	7	0.95
TPP/PEEOP	14.3	12	1.72	8	1.14
PHOSFLEX 4/PEEOP	15.4	12	1.85	5	0.77
RDP/PEEOP	15	8	1.2	8	1.2
-- 1.0 pcf Density --					
BTPP	8.5	17	1.45	17	1.45
BTPP/PEEOP	13.8	16	2.21	15	2.07
PEEOP	19	7	1.33	7	1.33

Data Set 2

The following data illustrates the parts per hundred of
 5 flame retardant (PEEOP and/or BTPP) needed to actually pass
 the MVSS 302 test and the TB 117 tests in a 1.5 density foam:

<u>Flame Retardant</u>	<u>MVSS 302</u>	<u>TB 117</u>
BTPP*:PEEOP	8	10
10 (1:1 Wt. Ratio)		
100% PEEOP	5	5
* available from Akzo Nobel Chemicals Inc. under the trademark PHOSFLEX 71B.		

15 The following additional data was obtained:

SAMPLE ID	Total % P to pass TB117	Total % P to pass MVSS302	Density 1.5 (pcf)	Air flow ft ³ /min
BTPP (estimate)	2.2	2.4	1.5	5
Blend: 1:1	1.38	1.1	1.49	5.2
PEEOP (neat)	0.95	0.95	1.51	5.2

From an analysis of all of the foregoing data, a number
 of conclusions can be reached: Generally speaking, an increase
 20 in the density of the foam will reduce the amount of flame
 retardant that is needed to pass a specific flame retardancy
 test.

There is a clear advantage to blending the PHOSFLEX 71B
 brand material with the PEEOP additive in a 1.8 density foam
 25 since the BTPP/PEEOP additives passes the TB 117 and MVSS 302
 test at 5 parts.

Data Set 3

The following data illustrates the parts per hundred of flame retardant (PEEOP and/or BTPP) needed to actually pass the MVSS302 test and the TB 117 tests in a 1.8 density foam and the theoretical, predicted amount.

	<u>Flame Retardant MVSS 302</u>	<u>Theoretical</u>	<u>TB 117</u>	<u>Theoretical</u>
10 100% BTPP	14	14	16	16.0
1 BTPP: 1 PEEOP	5	9	5	10.5
100% PEEOP	4	4	5	5.0

The following additional data was obtained:

SAMPLE	Total %P to pass TB117	Total % P pass MVSS302	Density 1.8 (pcf)	Air Flow (ft ³ / min)
BTPP (Neat)	1.36	1.19	1.82	4.2
Blend: 1:1	0.69	0.69	1.79	4.1
PEEOP (neat)	0.95	0.76	1.85	6.0

At 1.5 and 1.8 foam density, blends (1:1) of the BTPP:PEEOP additives showed improvement over use of the neat BTPP. The blends passed the TB-117 test at 5 parts in a 1.8 foam whereas the neat BTPP material passed at 16 parts. The
5 blend, while containing only 50% of the PEEOP component, is nearly as efficient as neat PEEOP (which passed at 5 parts in a 1.8 and 10 parts in a 1.5 density foam) but would be much cheaper to produce due to the amount of the cheaper BTPP material.

10 The 1:1 ratio of BTPP:PEEOP in a 1.8 density foam is of interest. The 1:1 ratio blend shows an advantage (pass: 5 parts in MVSS 302 test) over the use of the neat BTPP material (pass: 14 parts). It is also advantageous to use the 1:1 ratio material in 1.5 density foam. The BTPP-containing
15 sample passes at about 15-16 parts, whereas the 1:1 ratio BTPP:PEEOP blend passes at 8 parts.

Data Set 4

5 This Data Set illustrates the flammability efficiency of other monomers and a dimer blended with PEEOP flame retardants at 1:1 ratios in a 1.8 pcf density foam:

Flame Retardant	%P	TB117 (phr of FR)	%P to pass in foam	MVSS 302 (phr of FR)	%P to pass in foam
-- 1.8 pcf Density --					
BTPP	8.5	16	1.36	14	1.19
BTPP/PEEOP	13.8	5	0.69	5	0.69
PHOSFLEX 31P/PEEOP	13.5	7	0.94	4	0.54
TPP/PEEOP	14.3	7	1.00	4	0.57
PHOSFLEX 4/PEEOP	15.4	7	1.08	5	0.77
PEEOP	19	5	0.95	4	0.76
RDP/PEEOP	15	5	0.75	5	0.75

The foregoing Examples merely illustrate certain embodiments of the present invention and, for that reason should not be construed in a limiting sense. The scope of protection that is sought is set forth in the claims that follow.

We Claim:

1. A polyurethane foam that contains an effective amount
5 for flame retardancy of a flame retardant blend comprising:
(a) a non-oligomeric, non-halogenated organophosphorus flame
retardant that is adapted for use in a polyurethane foam
formulation; and (b) an oligomeric organophosphorus flame
retardant having a phosphorus content of no less than about
10 10%, by weight, and at least three phosphorus atom-containing
units therein.

2. A foam as claimed in Claim 1 wherein flame retardant
(a) in the blend is a non-halogenated phosphate ester
15 containing alkyl groups.


3. A foam as claimed in Claim 1 wherein flame retardant
(a) in the blend is a non-halogenated phosphate ester
containing aryl groups.
20

4. A foam as claimed in Claim 1 wherein flame retardant
(a) in the blend is a non-halogenated phosphonate-containing
composition.

25 5. A foam as claimed in Claim 2 wherein flame retardant
(a) in the blend is present at from about 25% to about 95%, by
weight of the blend.


6. A foam as claimed in Claim 3 wherein flame retardant (a) in the blend is present at from about 25% to about 95%, by weight of the blend.

5 7. A foam as claimed in any of Claims 1-6 wherein the oligomeric organophosphorus flame retardant is an oligomeric organophosphate flame retardant in the blend of the formula:



10 where n, on a number average basis, can range from 2 to about 20, and R is selected from the group consisting of alkyl and 15 hydroxyalkyl, and R' is alkylene.

8. A foam as claimed in any of Claims 1-6 wherein the oligomeric organophosphorus flame retardant is an oligomeric organophosphate flame retardant in the blend of the formula:



20 25 where n, on a number average basis, can range from 2 to about 20, and R and R' are ethyl and ethylene.

POLYURETHANE FOAM CONTAINING FLAME RETARDANT
BLEND OF NON-OLIGOMERIC AND OLIGOMERIC FLAME RETARDANTS

5 Abstract of the Disclosure

A polyurethane foam can be flame retarded by the incorporation therein of a flame retardant blend that comprises: (a) a non-oligomeric non-halogenated organophosphorus flame retardant (e.g., a phosphate ester) that is adapted for use in a polyurethane foam formulation; and (b) an oligomeric organophosphorus flame retardant (e.g., a phosphate ester) having a phosphorus content of no less than about 10%, by weight, and at least three phosphate ester units therein.

10

15

DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled: **POLYURETHANE FOAM CONTAINING FLAME RETARDANT BLEND OF NON-OLIGOMERIC AND OLIGOMERIC FLAME RETARDANTS**, the specification of which:

☒ is attached hereto, and/or

was filed on _____ as Application Ser. No.

☐ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above- identified specification, including the claims, as amended by any amendment referred to above. All factual statements made in the specification of my own knowledge are true and all factual statements made on information and belief are believed to be true.

I acknowledge to the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, Sec. 1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, Sec. 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

			<u>Priority Claimed</u>
			<u>Yes</u> <u>No</u>
_____ (Number)	_____ (Country)	_____ (Day/Month/Year)	_____ Yes No
_____ (Number)	_____ (Country)	_____ (Day/Month/Year)	_____ Yes No

I hereby claim the benefit under Title 35, United States Code § 119 of any provisional application(s) listed below:

None

I hereby claim the benefit under Title 35, United States Code, Sec. 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, Sec. 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, Sec. 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

Express Mail Label No.: EL246554616US

(Appln. Ser. No.) (Filing Date) (Status: patented, pending, abandoned)

(Appln. Ser. No.) (Filing Date) (Status: patented, pending, abandoned)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following as my attorneys of record, with full power of substitution and revocation, to prosecute this application and to transact all business in the Patent Office:

Richard P. Fennelly, Reg. No. 25,677
Ralph J. Mancini, Reg. No. 34,054
Joan McGillicuddy, Reg. No. 35,608


Louis A. Morris, Reg. No. 28,100
David H. Vickrey, Reg. No. 30,697
Lainie E. Parker, Reg. No. 36,123

Direct all correspondence to:

Richard P. Fennelly
Akzo Nobel Inc.
Patent and Trademark Department
7 Livingstone Avenue
Dobbs Ferry, NY 10522-3408
(914) 674-5464

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Sec. 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first inventor: Larry L. Bradford

Inventor's signature 

Date September 3, 1999

Residence 28 Rolf's Drive, Danbury, Connecticut 06810

Citizenship United States of America

Post Office Address (Same as Above)

Post Office Address (Same as Above)Post Office Address (Same as Above)Post Office Address (Same as Above)